



# V PERLITE 2A

## MINERAL FILTRATION ADJUVANT

### COMPOSITION



Expanded perlite, highly pure.

### CHEMICAL - PHYSICAL CHARACTERISTICS



Moist panel density	0,190 - 0,230 kg/L
Floating 20 g/250mL	≤ 32 mL
Permeability	2 - 3 Darcy

### APPLICATIONS



V PERLITE 2A is the ideal product for the first filtration of musts by using rotary vacuum filters.

It is recommended also in the filtration of beer, juices, sugar, water, oils for food use, enzymes, pharmaceutical products and organic products.

**When using V PERLITE 2A comply with the relative legal regulations in force.**



# V PERLITE 2A

## MINERAL FILTRATION ADJUVANT



### DOSAGE

From 1000 to 1500 g per m<sup>2</sup> in the formation of the panel on the drum of the vacuum filter (vacuum).

The quantity of V PERLITE 2A can change according to the height of the panel desired; recommended to use it in association with the pre-coat V CELL<sup>®</sup> VACUUM.



### PACKAGING

16 kg bags.



### STORAGE

Keep in a cool and dry place.  
Carefully re-seal open packages.



### HAZARD

Based on the current European regulations the product is classified: not hazardous.